

Biresin® CR170 with Biresin® CH125-1 hardener
Composite resin system**Areas of Application**

- For injection processing

Product Benefits

- Short cycle times for RTM processing
- Glass transition temperatures up to 116°C dependent on curing conditions

Description

- Basis Two-component-epoxy-system
- Resin (A) **Biresin® CR170**, epoxy resin, colourless to yellowish
- Hardener (B) **Biresin® CH125-1**, amine, colourless to yellowish

Physical Data		Resin (A)	Hardener (B)
Individual Components		Biresin® CR170	Biresin® CH125-1
Viscosity, 25°C	mPas	13,000	< 10
Density, 25°C	g/ml	1.14	0.98
Mixing ratio	in parts by weight	100	25
		Mixture	
Potlife, 100 g / RT, approx. values	min	24	
Mixed viscosity, RT, approx. values	mPas	1,250	

Mechanical Data of neat resin specimen

Biresin® CR170 resin (with hardener (B)			Biresin® CH125-1	
Curing conditions			9 min 110°C	2 h 120°C
Shore hardness	ISO 868	-	D 85	D 84
Flexural E-Modulus	ISO 178	MPa	2,500	2,500
Tensile E-Modulus	ISO 527	MPa	2,400	2,400
Flexural strength	ISO 178	MPa	104	107
Tensile strength	ISO 527	MPa	74	77
Elongation at break	ISO 527	%	8.4	8.1
Impact resistance	ISO 179	kJ/m²	86	91

Processing

- The temperature of the resin system should be 30 - 40°C to achieve good mixing of components.
- The processing temperature of the mould should be between 60 and 120°C.
- To clean brushes or tools immediately Sika Reinigungsmittel 5 is recommended.
- Additional information are available in "Processing Instructions for Composite Resins".

Packaging

Individual components	Biresin® CR170 resin (A)	200 kg; 30 kg, 10 kg net
	Biresin® CH125-1 hardener (B)	180 kg; 3 kg net

Thermal Data of neat resin specimen				
Biresin® CR170 resin (A)		with hardener (B)	Biresin® CH125-1	
Curing conditions		time temperature	9 min 110°C	2 h 120°C
Heat distortion temperature	ISO 75B	°C	110	114
	ISO 75C	°C	85	102
Glass transition temperature	ISO 11357	°C	110	116

Storage

- Minimum shelf life of Biresin® CR170 resin (A) is 24 month and of Biresin® CH125-1 hardener (B) is 12 month under room conditions (18 - 25°C), when stored in original unopened containers.
- After prolonged storage crystallisation of resin may occur. This is easily removed by warming up for a sufficient time to 60-70°C.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safetyrelated data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Further information available at:

Sika Deutschland GmbH
Subsidiary Bad Urach
Stuttgarter Str. 139
D - 72574 Bad Urach
Germany

Tel: +49 (0) 7125 940 492
Fax: +49 (0) 7125 940 401
Email: tooling@de.sika.com
Internet: www.sika.com

